

TECHNICAL DATASHEET

STALOC MS HYBRID PLUS

white

PRODUCT DESCRIPTION

STALOC MS Hybrid PLUS is an ideal assembly adhesive with extremely high initial adhesion and grab. STALOC MS Hybrid PLUS is suitable for making elastic constructive joints, which require a high strength.

STALOC MS Hybrid Plus is based on Silyl Modified Polymer (SMP).

PRODUCT FEATURES

- Extreme high initial tack
- Solvent-, isocyanate-, silicone- and PVC-free
- Very good resistance against UV-radiation and ageing
- Permanently elastic within temperatures from -40°C till +100°C
- Neutral, odourless and fast curing
- Paint compatible with most industrial paint- or lacquer systems, both alkyd resin and dispersion based (due to the large scale of different types of industrial paints a paint compatibility test is recommended)
- Paintable after skin forming (wet on wet); this will not influence the curing speed

AREAS OF APPLICATION

- Elastic bondings and sealings in e.g. bus-, caravan-, train- and truck construction
- Bonding and sealing of sunroof systems
- Bonding of roofs on busses, trains, trucks
- Bonding of corner profiles of aluminium or polyester on trailers
- Bonding of polyester parts on metal frames
- Bonding of floor systems
- Bondes stone (not porous), cement, mirror, natural stone, cast, polycarbonate, PSPU, PVC, several synthetic materials, ceramic flags, enamel, copper, lead, zinc, aluminium, stainless steel, painted surfaces, wood, glass, polystyrene, etc.

Before applying STALOC MS Hybrid we recommend to use STALOC Assembly Cleaner for surface preparation.

Apply on clean, grease-and dust-free surface, without a primer. Excellent adhesion can be obtained on powder coated surfaces, metals, glass, mirrors, ceramics, non-porous surfaces in general and various plastics. The broad variety of applications of STALOC MS Hybrid makes it necessary to determine adhesion between various substrates by experiment.

- Substrate temperature for bonding process: between +5°C and +60°C.
- Application temperature: between +5°C and +40°C.

Not suitable for bonding PE, PP, Teflon (PTFE) and bitumen-substrates. Not suitable for direct contact with PVB-layers. Might show yellowing effect in dark surroundings.

TECHNICAL ATTRIBUTES

ATTRIBUTE	UNIT	SPECIFICATION
chemical basis		silyl modified polymer (SMP)
consistency		thixotropic
colour	UNIT	white
Curing in 24 hours	mm	3,0
skin forming time	mm	after ~ 10 min.
shore A Hardness (DIN 53505)		58
elongation at break (DIN 535304)		355%
100 % Modulus (DIN 53505)	MPa	1.39 MPa
tensile strength (DIN 53504)	MPa	2.18 MPa
MZV (ISO 9040)		25%
shrinkage	%	None
density at +25°C	kg/m ²	1,569
shelf life at +25°C	months	12

SAFETY INFORMATION

Please send your request for the latest version of the material safety data sheet (MSDS).

PACKAGING / VOLUME

290 ml per cartridge / 20 pcs. per box

The information and data in this document are for information purposes only. STALOC cannot take responsibility for the results obtained by a third party, whose methods are not under STALOC control. The determination of the suitability for the user's purpose of any STALOC product is the responsibility of the client. Consequently, STALOC recommends testing of the products before using it for a series application. Moreover, it is the responsibility of the customer to ensure a safe environment for the user. STALOC therefore disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of STALOC products. STALOC cannot be held liable for any consequential or incidental damage resulting from the use of a STALOC product, including lost profits or damages of any other kind. Products or processes mentioned herein might be subject to released or pending patents or licences.

Issued: 04.02.2013



call STALOC



www.staloc.com

